


## Commercial Nitrile Rubber Sheetting 70° Shore

Product Code: RC0339

### Product Description

Our commercial nitrile rubber sheetting is a cost efficient material that is suitable for use in a wide variety of light to medium use applications. It is able to provide similar physical properties found in our premium-grade materials at a fraction of the price. This product is perfect for everyday applications, where the material will not come under much duress.



Available In -



Full Rolls

Cut to strip

Bespoke  
Gaskets

### Technical Specification

Properties	Test Method	Values
Product	-	Commercial Nitrile Rubber Sheetting
Compound	-	NBR
Hardness (Shore A)	ISO 7619-1	70° ± 5°
Density	ISO 2781	1.4 g/cm <sup>2</sup>
Tensile Strength	ISO 37	5 N/mm <sup>2</sup>
Elongation at Break	ISO 37	300%
Compression Set (22h, 70°C)	ISO 37	35%
Working Temperature Range	-	-28°C to + 80°C



ISO  
9001 : 2015  
REGISTERED

The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.

### Standard Sizes

Properties	Tolerances
1mm x 1.4m x 10m	+/- 0.2mm
1.5mm x 1.4m x 10m	+/- 0.3mm
3mm x 1.4m x 10m	+/- 0.3mm
4mm x 1.4m x 10m	+/- 0.4mm
5mm x 1.4m x 10m	+/- 0.4mm
6mm x 1.4m x 10m	+/- 0.5mm

### Made To Order Sizes - Subject To Minimum Order Quantities

Properties	Tolerances
0.5mm x 1.4m x 10m	+/- 0.2mm
8mm x 1.4m x 5m	+/- 0.7mm
10mm x 1.4m x 5m	+/- 1mm
15mm x 1.4m x 5m	+/- 1mm
20mm x 1.4m x 5m	+/- 1.4mm
25mm x 1.4m x 5m	+/- 1.75mm
32mm x 1m x 1m	-
38mm x 1m x 1m	-
40mm x 1m x 1m	-



The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.