

## 南京宇航橡胶有阻公司 NANJING YUHANG RUBBER CO.LTD

Manufacturers · Designers · Distributors

## Black Closed Cell EPDM Sponge Material Datasheet

Product Code: RC02107-2020 S.C. REF: TRC03

## **Key Feautres**

Our EPDM sponge rubber is a high-quality, closed cell material that is commonly used to create an air and watertight seal. EPDM sponge is great for use in outdoor sealing applications due to the superior UV and Ozone resistance it provides. Apart from offering excellent weathering resistance, EPDM also features good flexibility and tensile strength properties.



## **Technical Specification**

| Properties   | Test Method   | Values                   |
|--|---------------|--------------------------|
| Product  | -             | Closed Cell EPDM Sponge  |
| Compound   | -             | EPDM                     |
| ASTM D1056-14 Classification                         | 2A2 B3 M      | -                        |
| Hardness (Shore 00)                                  | -             | 50°-60°                  |
| Density  | ASTM D3575    | 180-200 kg/m³            |
| Tensile Strength                                     | ASTM D412     | 780-850 kPa              |
| Elongation at Break                                  | ASTM D412     | 140-180%                 |
| Compression Set (25%, 22hrs @ 23°C)                  | ASTM D1056    | 4-5%                     |
| Shrinkage (22hrs @ 70°C)                             | ASTM D573     | 4-8%                     |
| Compression Deflection (25%)                         | ASTM D1056    | 50-70 kPa                |
| Compression Deflection (50%)                         | ASTM D1056    | 100-120 kPa              |
| Temperature Range (Constant)                         | -             | -30°C to +90°C           |
| Temperature Range (Intermittent)                     | -             | +100°C                   |
| Water absorption (Max Weight Change)                 | ASTM D1056    | 1-2 %                    |
| Flame Resistance (>3mm)                              | FMVSS302      | Pass                     |
| Ozone Test (200 +/- 5 pphm, 20%, 72hrs @ 40 +/- 2°C) | ASTM D1171-99 | No Cracks                |
| Environmental Protection                             | -             | CFC, Halogen & HCFC Free |

The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.